

Application No. 10/747,616  
Response to Office Action mailed January 24, 2007  
Atty. Dkt. No.: C261.1040.1

**In the Claims:**

This listing of claims will replace all prior versions, and listings of claims in the application.

1. (Previously Presented)	A coating material comprising:
Alkyd/Epoxy resin	24-48%
TiO <sub>2</sub>	24-48%
Talc	9-22%
Calcined Clay	>0-30%
Catalyst	0-1%
Colorant	0-1%
Barytes	0-5%
Solvent q.s., and reaction products therof.	

2. (Original) The coating material according to claim 1, wherein the amount of calcined clay is at least 4%.

3. (Cancelled).

4. (Previously Presented) The coating material of claim 1, wherein the coating material is based on alkyd.

Claims 5-20 (Cancelled)

21. (New) A food grade coating material comprising:

100-200 parts by weight of an alkyd or epoxy resin,  
100-200 parts by weight of TiO<sub>2</sub>,  
20-50 parts by weight of Talc, and  
0-30 parts by weight Calcined clay,  
solvent q.s.,

Application No. 10/747,616  
Response to Office Action mailed January 24, 2007  
Atty. Dkt. No.: C261.1040.1

and reaction products thereof.

22. (New) The food grade coating material of Claim 21, further comprising an anti-scuffing agent.

23. (New) The food grade coating material of Claim 21, further comprising an anti-foaming agent.

24. (New) The food grade coating material of Claim 21, further comprising a dispersing aid.

25. (New) The food grade coating material of Claim 21, further comprising a flow control agent.

26. (New) The food grade coating material of Claim 21, in the form of a film.